

TEST REPORT

Geo Quarries Ltd
Prestige Court
Beza Road
Leeds
LS10 2BD



White
Rose
Laboratory
Services
Ltd

Lumley St • Castleford • WF10 5LB
01977 520625 • enquiries@whiteroselabs.co.uk

Report WRL/25/2088la
Issue date 23/12/25

Material	10-14mm Crushed Limestone*	Sample N°	S/25/2088
Site	Little Ponton Quarry*	Sampled by	Client
Specification	-	Date sampled	Not Stated
Source	Little Ponton Quarry*		
Supplier	Geo Quarries Ltd*		
Sample location	Not Stated	Date received	10/12/25
Sample type	Bulk	Date tested	18/12/25

BS EN 1097-2 2020 Los Angeles Coefficient

The test portion was obtained from the 10 - 11.2 and 11.2 - 14 mm size fractions

L A Coefficient 38

Deviations From Procedure

**Insufficient mass supplied (9Kg), all material used for test.

All testing carried out at White Rose Laboratory Services Ltd, Lumley Street, Castleford

Test results relate only to items tested. Results apply to sample as-received.

*denotes information supplied by client

M O'Hara
Laboratory Operations Manager

RT015/25/01

This test report shall not be reproduced, except in full, without the written approval of White Rose Laboratory Services Ltd